

ACRONI

255768

ACRONI, d.o.o.
Cesta Borisa Kidriča 44
SI - 4270 Jesenice
T. +386 4 584 10 00
F. +386 4 584 11 11
E: uprava@acroni.si
W: http://www.acroni.si

<p>Potrđilo o prevzemu 3.1 / Abnahmeprüfzeugnis 3.1 / Inspection Certificate 3.1 EN 10304 3.1 Stran/Strik/Page 1/2 Št./Nr./No. Datum/Datum/Data 31067732-1 30 /8/2006</p> <p>Naročnik/Bestellung/Order: CFF_080756 duso,24169 Izdelek/Erzeugnis/Product: Plates</p> <p>Dobavni list/Lieferchein/Despatch N. 31067732 from 30.8.2006 Vrsta peči/M. Furnace: E+VOD</p>	<p>Naročnik/Kunde/Customer CFF STAINLESS STEELS INC. HAMILTON 1840 BURLINGTON EAST LGH 3L4 ONTARIO CANADA</p>
--	--

	Znak izvedenca TK	Znak proizvajalca
--	-------------------	-------------------

Specifikacije/Vorschriften/Specifications ASTM A 240/A 240M/ED 04, ASTM A 480 ASME SA 240 SECT. II PART A/ED-01 QQS-776D	Tip/W.Nr./Type 304L/304 304L/304	Pov./Fläche/Finish No.1 No.1	Kor.test/Int.krist.korr./Corrosion test ASTM A262 PRACTICE E0K
---	--	------------------------------------	---

Obseg dobave / Umfang der Lieferung / Extent of mat. delivery

Poz./Pos./Item	Sarta/Schmelzen Nr./cast No.	Št. plošte/Walztafel /Plate No	Teža/Gewicht/ Weight	Dimenzije/Abmessungen/Dimensions	Št. Stuk/Q	Št. Vp. Nr.
3	255783	72416 ✓	1858	0.750x78.74x240	1	72415
5	255782	72443 ✓	3097	1.250x78.74x240	1	72443
5	255782	72445 ✓	3097	1.250x78.74x240	1	72445
12	255768	71339 ✓	5284	3.250x78.74x157.50	1	71339
14	255768	71336 ✓	4878	4.000x78.74x118.14	1	71336
14	255768	71337 ✓	4878	4.000x78.74x118.14	1	71337

Mehanske lastnosti/Mechanische Eigenschaften/Mechanical properties

Št. vzorca Sample No.	Smer vzorca Position	Nap. točenja 0.2 % Yield 0.2% N/mm2	Nap. točenja 1% Yield 1% N/mm2	Nat. Trdnost Tensile N/mm2	Raztez ož A5 % Elongation	Raztez ek A80% Elongation	Raztez ek A80% Elongation	Trdota Hardness HB	Zil.1 Impact J	Zil.2 Imp act J	Zil.3 Imp act J	Tem. p °C	Št. vzorca Sample No.
72415	P	315	366	624	75.8			174		358	368	374	20
72443	P	316	363	634	71.0			174		353	365	344	20
72445	P	318	362	616	72.6			174		352	341	335	20
71339	P	337	391	643	68.5			163		325	324	336	20
71336	P	295	340	589	78.3			167		345	352	359	20
71337	P	293	338	584	77.2			167		359	326	351	20

Sij Slovenska industrijska jela

ACRONI
ACRONI, d.o.o.
Cesta Borisa Kidriča 44, 4270 Jesenice
Slovenija

89157, 89158, 89159, 89160-1

ACRONI

ACRONI, d.o.o.
Cesta Borisa Kidriča 44
SI - 4270 Jesenice
T: +386 4 584 10 00
F: +386 4 584 11 11
E: uprava@acroni.si
W: http://www.acroni.si

Potrdilo o prevzemu 3.1 / Abnahmeprüfzeugnis 3.1 / Inspection Certificate 3.1

Št./Nr./no. : **31067732-1**

Stran/Seite/Page 2/2

Kemična analiza/Chemische Zusammensetzung/Chemical composition

Sarža	%C	%Si	%Mn	%P	%S	%Cr	%Co	%Ni	%Mo	%Ti	%N	%B
255768	0.020	0.28	1.38	0.039	0.001	18.11		8.10			0.0985	
255782	0.022	0.32	1.57	0.038	0.002	18.14		8.08			0.0953	
255783	0.023	0.29	1.65	0.034	0.002	18.63		8.24			0.0989	

Opombe/Remarks

BENDING TEST : GOOD
FREE FROM KNOWN CONTACT WITH MERCURY.
INTERGRANULAR CORROSION TEST PER ASTM A 262 PRACTICE E-93a : GOOD!
GRAIN SIZE PER ASTM E 112 PASSED : 7-8
NO WELD REPAIRS

C.I.F.F. STAINLESS STEELS S/O# 37713 LOT V-1 *[Signature]*

sj
Slovenska industrija jekla
skupina

ACRONI
ACRONI, d.o.o.
Cesta Borisa Kidriča 44, 4270 Jesenice
Član skupine SI
Member of Group
Številna mesta: 19417200
Članski listič: 8 616 232 144 40 01
Kontakt: 040 420 1111
Izpolni: 1421940731

89157 89158 89159 89160-2