

HT# 61720



Tel. (+39).(030).6829911  
 Fax. (39).(030).6820616  
 Via Industriale, 1 - 25021 BAGNOLO MELLA (BS) ITALY

**CERTIFICATE OF QUALITY AND MATERIAL TESTING**

INSPECTION CERTIFICATE N. **AC/ 4058** DATE : 19/12/17  
 according to EN 10204.3.1

FIRM :  
 ORDER : P05025 ORDER CONFIRMATION : 205831

HEAT	N. of PCS	MATERIAL DESCRIPTION	MATERIAL GRADE
61720	3	FORGED ROUND PEELED BARS Ø13"	316/316L UNS S31600 /S31603 SS1 Rev.5 ASTM A276-17 ASTM A479-17 ASTM A484-15 ASME Code Sec.II Part. A SA479-15 AMS 5653H AMS QQS 763D Cond.A AMS 5648M AMS S-7720 316 NACE MR 0103-15 NACE MR 0175/ISO 15156-2015
		Lbs 8699,448 x 18,43176 feet Lbs 8886,841 x 18,83858 feet Lbs 9358,631 x 19,78675 feet	

H.T. CONDITION: Solution annealed 1050°C (6h) + water quenched

HEAT ANALYSIS									
C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Sn (ppm)
0,016	1,81	0,26	0,025	0,0274	17,10	10,17	2,03	0,391	<100
Ca	Al	V	Ti	W	Ta	As (ppm)	Co	Nb	Pb (ppm)
0,0064	0,007	0,035	0,002	0,034	0,0034	<20	0,053	0,028	<1
B	N	Zr	Sb	Fe	PRE	Ferrite (%) ASTM E562	Grain size ASTM E112		
0,0001	0,054						5		

TEST RESULTS ON ACTUAL BAR PROLONGATION								
Temp. [°C]	Direction	Rp0.2 [KSI]	Rm [KSI]	A [%]	Z [%]	KV (10 X 10 mm) [J]	Hardness	
RT	L	38	79	46,8	56,2		HBw 157 HRc 2	

Steelmaking process E.A.F. + A.O.D. refining  
 No welding performed on material  
 Material free from Mercury contamination  
 Material inspected with a gamma spectrometer and with no radioactive contamination beyond the limits provided for by the EU-Radiation Protection 122- part 1, when relevant  
 Mechanical tests performed according to ASTM A370-17 (Ø12,5mm-50mm length) + ASTM E10-17 + ASTM E18-17  
 Corrosion test according to ASTM A262 Pr.E satisfactory performed  
 Chemical analysis and mechanical properties according to ASTM A182-17-ASME SA182-15 (F316-F316L) - ASTM A193-16 - ASME SA193-15 (Grade B8M Class 1)  
 Country of melt and country of manufacture: Italy  
 Italfond is in compliance with DFARS regulation 252.225-7017  
 Forging ratio 4,2:1  
 PMI performed

SURVEYORS	CUSTOMER INSPECTION	ITALFOND S.p.A. Quality Assurance
		 <b>GARANZIA QUALITA'</b>

C208279 1/3



Tel. (39).(030).6829911  
 Fax. (39).(030).6820616  
 Via Industriale, 1 - 25021 BAGNOLO MELLA (BS) ITALY

**CERTIFICATE OF QUALITY AND MATERIAL TESTING**  
**MICROGRAPHIC EXAMINATION**

INSPECTION CERTIFICATE N. **ME/ 4058** DATE : **19/12/17**  
 according to EN 10204.3.1


FIRM :  
 ORDER : **P05025** ORDER CONFIRMATION: **205831**

HEAT	N. of PCS	MATERIAL DESCRIPTION	MATERIAL GRADE
61720	3	FORGED ROUND PEELED BARS Ø13"  Lbs 8699,448 x 18,43176 feet Lbs 8886,841 x 18,83858 feet Lbs 9358,631 x 19,78675 feet	316/316L UNS S31600 /S31603 SS1 Rev.5 ASTM A276-17 ASTM A479-17 ASTM A484-15 ASME Code Sec.II Part. A SA479-15 AMS 5653H AMS QQS 763D Cond.A AMS 5648M AMS S-7720 316 NACE MR 0103-15 NACE MR 0175/ISO 15156-2016

H.T. CONDITION : Solution annealed 1050°C (6h) + water quenched

**MICROGRAPHIC EXAMINATION - MID RADIUS**

Magnification: 100 x  
 Etching: electrolytic, Oxalic Acid 3v 90s according to ASTM E407



**RESULT: Omogeneous structure free from detrimental phases and precipitates**

SURVEYORS	CUSTOMER INSPECTION	ITALFOND S.p.A. Quality Assurance
		 <b>GARANZIA QUALITA'</b>

C208279 2/3

**CERTIFICATE OF QUALITY AND MATERIAL TESTING**  
**MACROGRAPHIC EXAMINATION**

INSPECTION CERTIFICATE N. **ME2/ 4058** DATE : **19/12/17**  
 according to EN 10204.3.1

FIRM :


ORDER : **P05025** ORDER CONFIRMATION: **205831**

HEAT	N. of PCS	MATERIAL DESCRIPTION	MATERIAL GRADE
61720	3	FORGED ROUND PEELED BARS Ø13"  Lbs 8699,448 x 18,43176 feet Lbs 8886,841 x 18,83858 feet Lbs 9358,631 x 19,78675 feet	316/316L UNS S31600 /S31603 SS1 Rev.5 ASTM A276-17 ASTM A479-17 ASTM A484-15 ASME Code Sec.II Part. A SA479-15 AMS 5653H AMS QQS 763D Cond.A AMS 5648M AMS S-7720 316 NACE MR 0103-15 NACE MR 0175/ISO 15156-2015

H.T. CONDITION : Solution annealed 1050°C (6h) + water quenched

**MACROGRAPHIC EXAMINATION**

Etching: 50% H<sub>2</sub>O + 50% Hcl



SURVEYORS	CUSTOMER INSPECTION	ITALFOND S.p.A. Quality Assurance
		 <b>GARANZIA QUALITÀ</b>

C908279 3/3