

VIRAJ PROFILES LIMITED

10 Imperial Chambers, 1st Floor,
Wilson Road, Mumbai 400 038
INDIA

VIRAJ 16

CO14525

82910

TEST CERTIFICATE

ORDER NO	PACKING LIST NO	INSPECTION NO	DATE
P00998	IMP/911847/14	10000546733	22.04.2010
		GRADE	HEAT No
		316/316L	82910

BUNDLE NO:
5186332 ,5186331 ,5186330 ,5186329 ,5186328 ,

DESCRIPTION
STAINLESS STEEL BRIGHT BARS

SMOOTH TURNED

SIZE	SHAPE	TOLERANCE	LENGTH	PIECES	WEIGHT
3 3/4"	ROUND	ASTM A484	12' - 14'	11	5,313.000 LB

CHEMICAL ANALYSIS

%C	%Mn	%Si	%S	%P	%Cr	%Ni	%Cu	%Mo	%Co	%N2
0.0200	1.860	0.440	0.0200	0.0390	16.280	10.040	0.400	2.040	0.160	0.0750

TEST RESULTS

0.2% yield strength ksi	Tensile Strength ksi	Elongation %	Reduction Of Area %	Area Hardness BHN	Grain Size NOS
42.0	84.0	58.0	72.0	170.0	6.0


SPECIFICATION:

MATERIAL CONFIRMS TO DIN EN 10088-3:2005: 1.4401/1.4404.
EN 10222-5 AND EN 10272 COND-A & ASTM A182/A-182M-06, A276-06 COND A, A479/A479M-06a COND A, A193/A193M-06a B8M CL-1, A320/A320M-05a B8M CL-1, A484-06b, A388/A388M-05, ASME SA182-04, SA479-04, SA 193-04 B8M CL-1, SA320-04 B8M CL-1, ASTM A314-2002 IGC SATISFACTORY AS PER ASTM A 262-02a PRACTICE E, AMS 5648J / AMS 5653F (EXCEPT MARKING), QQ-S-763F, NACE-MR0175-2002, SAB-AMS-S-7720A, MIL-S-862 B, AISI 316/316L & UNS#S31600/S31603. CERTIFICATION AS PER EN 10204-3.1.

REMARKS

MATERIAL IS FREE FROM MERCURY CONTAMINATION, FREE FROM WELD OR WELD REPAIRS, MICRO-FREE FROM CONTINUOUS CARBIDE NETWORK ON GRAIN BOUNDARIES, MACRO-GOOD, MINIMUM SOLUTION ANNEALING TEMPERATURE 1050C, SOAKING TIME 10 HRS, WATER QUENCHED. MELT SOURCE: AOD. WE CONFIRM THAT THE MATERIAL HAS BEEN TESTED AND FOUND TO BE FREE FROM RADIOACTIVE CONTAMINATION. COUNTRY OF ORIGIN: INDIA.

We hereby certify that the material described above has been tested and complies with the terms of order/contract.



Suvarna

WORKS INSPECTOR
S. SUVARNA.