96895

PJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

Contract No.: 50005
TECHN.PROTOCOL № 390-11 SPEC.№3756/P012905-TO
DIN EN 10088-3-05,DIN EN 10272-08,DIN EN 10222-5-00;AD2000-Merkblatt W2;AD 2000-Merkblatt W10;ASTM A182/A182M-10;ASME SA-182/SA-182M-10;ASTM A276-10;ASTM A314-08,ASTM A479/A479M-10;ASME SA-479/SA-479M-10;ASTM A484/A484M-10;AMS-QQ-S-763B-06 Cond.A;AMS 5648K-07;AMS 5653F-07;ASTM A193/A193M-10GR B8M,CL1; ASME SA-193/SA-193M-10 GR B8,CL 1 ;ASTM A320/A320M-08 GR B8M,CL 1;ASME SA-320/SA-320M-10 GR B8,CL1;NACE MR 0175-03;NACE MR 0103-10

Sheets:8 Sheet: 4
QUALITY CERTIFICATE EN10204/3.1 Nr.253359
PLANT ORDER № 8014903756

QMS Certified

CUSTOMER
DSS INTERNATIONAL
SA Switzerland

PRODUCT DESCRIPTION
Bars and rods of corrosion-resistant (stainless) steel forged, peeled.Прутки из коррозионностойких (нержавеющих) сталей кованые, обточенные.
STEEL MAKING PROCESS: EAF+AOD
СПОСОБ ВЫПЛАВКИ:Электродуговая печь+АКР
Round 8.000in/203.20 mm L=4.715m/15.459ft
Grade: 316/316L/1.4404/1.4404

QUANTITY:
(number of pcs) 1bund Q-2809 lb/1274 kg

Delivery condition
solution annealed :1900° F(1040°C)water 15minutes
термообработка:закалка в воду

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N_2	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00--13.00	2.00--2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № 96895	.021	.42	1.36	.034	.023	16,78	10.11	2.08	.058	.23	.04	.09	.07	.08	.01	.028	.009	.001

DIN EN 10002-1,ASTM A370-09

MECHANICAL PROPERTIES	Yield Strength, (N/mm²) R0,2% R 1.0%		Tensile Strength, Rm, (N /mm²)	Elongation A e% L. O	Elongation In 2 inches (50mm) or 4D,min,% L.	Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J L	Impact strength, KV, J Q
REQUIRED	205	240	515-700	45 35	40	50	140-223	100	60
EFFECTIVE	262	294	539	61 52	56	75	159	212 212 219	61 61 61

Mechanical properties tested in state of delivery

US - testing	yes	Results: ASME SA-388/SA-388M-10(ASTM A 388/A 388M-09)-FBH1/8";EN 10228-4 type 1acclass 3:OK

Radiation free; mercury free. No Weld or Weld repair.

TECHNICAL REQUIREMENTS:
Macrostructure – GOOD
GRAIN SIZE : 5 to ASTM E 112-96(2004)
Nonmetallic inclusions ASTM E 45-05 (Method A)

A		B		C		D	
thin	thick	thin	thick	thin	thick	thin	thick
3.0	2.0	2.5	2.0	0.0	0.0	1.0	1.0

ICC-ASTM A262-08 (practice E)-test: O.K.
Dimension/surface defects test, anti-mixing test – OK

Manufacturer:PJSC DNIPROSPETSSTAL
Date: 05.10.11 Manager of quality assurance department - V. Kapaiev
Signed:

Zaporozhye
Made in Ukraine.

ДНІПРОСПЕЦСТАЛЬ ВАТ завод ТЕХНІЧНОГО КОНТРОЛЮ Україна м.Запоріжжя

0040615