



97749 (16").

CO 58666

PJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 50005 TECHN.PROTOCOL № 210-11 SPEC.№ 5867/P026485-ED ASTM A182/A182M-10;ASME SA-182/SA-182M-10;ASTM A276-10;ASTM A314-08;ASTM A479A479M-10;ASME SA-479/SA-479M-10;ASTM A484/A484M-10;AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07;AMS 5653F-07;ASTM A193/A193M-10 GR B8M,CL1 (EXC PAR 7.2);ASME SA-193/SA-193M-10GR B8M,CL1(EXC PAR 7.3);NACE MR 0175-03;NACE MR 0103-10										Sheets:9 Sheet: 6																																																																														
	CUSTOMER DSS INTERNATIONAL SA Switzerland										QUALITY CERTIFICATE EN10204/3.1 Nr.260934 PLANT ORDER № 8014905867																																																																														
	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel forged, peeled Прутки из коррозионностойких (пержавеющих) сталей кованные, обточенные STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 10.0in/254.00mm L=4.850m/15.902ft; 4.570m/14.984ft Grade: 316/F316/316L/F316L										QUANTITY: 1bund Q-4420 lb/2005 kg (number of pcs) 1bund Q-4198 lb/1904 kg																																																																														
	Delivery condition Solution annealed :1900-2010 ^o F(1040-1100 ^o C)/water/25 minytes термообработка:закалка в воду/25 мин.																																																																																								
<table border="1"> <thead> <tr> <th>ANALYSIS, %</th> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Al</th> <th>Cu</th> <th>V</th> <th>W</th> <th>Ti</th> <th>Co</th> <th>Nb</th> <th>N₂</th> <th></th> <th></th> </tr> </thead> <tbody> <tr> <td>REQUIRED</td> <td><.030</td> <td><1,00</td> <td>1.25-2.00</td> <td><.040</td> <td>.020-.030</td> <td>16.00-18.00</td> <td>10.00-14.00</td> <td>2.00-3.00</td> <td><.10</td> <td><.40</td> <td><10</td> <td><.20</td> <td><.15</td> <td><.40</td> <td><.20</td> <td><.10</td> <td></td> <td></td> </tr> <tr> <td>CAST № 97749</td> <td>.026</td> <td>.27</td> <td>1.37</td> <td>.036</td> <td>.025</td> <td>16,70</td> <td>10.23</td> <td>2.06</td> <td>.056</td> <td>.26</td> <td>.04</td> <td>.10</td> <td>.094</td> <td>.08</td> <td>.011</td> <td>.0520</td> <td></td> <td></td> </tr> </tbody> </table>																		ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N ₂			REQUIRED	<.030	<1,00	1.25-2.00	<.040	.020-.030	16.00-18.00	10.00-14.00	2.00-3.00	<.10	<.40	<10	<.20	<.15	<.40	<.20	<.10			CAST № 97749	.026	.27	1.37	.036	.025	16,70	10.23	2.06	.056	.26	.04	.10	.094	.08	.011	.0520																	
ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N ₂																																																																									
REQUIRED	<.030	<1,00	1.25-2.00	<.040	.020-.030	16.00-18.00	10.00-14.00	2.00-3.00	<.10	<.40	<10	<.20	<.15	<.40	<.20	<.10																																																																									
CAST № 97749	.026	.27	1.37	.036	.025	16,70	10.23	2.06	.056	.26	.04	.10	.094	.08	.011	.0520																																																																									
<table border="1"> <thead> <tr> <th colspan="7">ASTM A370-08a</th> <th colspan="11">TECHNICAL REQUIREMENTS:</th> </tr> <tr> <th>MECHANICAL PROPERTIES</th> <th>Yield Strength, Ksi(N/mm²) Re (R_{0.2})</th> <th>Tensile Strength, Rm,ksi (N /mm²)</th> <th>Elongation A₅ %</th> <th>Reduction of area, Z %</th> <th>Brinell Hardness HB</th> <th>Impact strength, KV, J</th> <th colspan="11"> Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 2.0 1.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK </th> </tr> </thead> <tbody> <tr> <td>REQUIRED</td> <td>36(248)</td> <td>75 (515)</td> <td>45</td> <td>50</td> <td>140-223</td> <td>100</td> <td colspan="11"></td> </tr> <tr> <td>EFFECTIVE</td> <td>38.0(258)</td> <td>82.9(570)</td> <td>59</td> <td>75</td> <td>167</td> <td>195</td> <td colspan="11"></td> </tr> </tbody> </table>																		ASTM A370-08a							TECHNICAL REQUIREMENTS:											MECHANICAL PROPERTIES	Yield Strength, Ksi(N/mm ²) Re (R _{0.2})	Tensile Strength, Rm,ksi (N /mm ²)	Elongation A ₅ %	Reduction of area, Z %	Brinell Hardness HB	Impact strength, KV, J	Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 2.0 1.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK											REQUIRED	36(248)	75 (515)	45	50	140-223	100												EFFECTIVE	38.0(258)	82.9(570)	59	75	167	195											
ASTM A370-08a							TECHNICAL REQUIREMENTS:																																																																																		
MECHANICAL PROPERTIES	Yield Strength, Ksi(N/mm ²) Re (R _{0.2})	Tensile Strength, Rm,ksi (N /mm ²)	Elongation A ₅ %	Reduction of area, Z %	Brinell Hardness HB	Impact strength, KV, J	Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 2.0 1.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK																																																																																		
REQUIRED	36(248)	75 (515)	45	50	140-223	100																																																																																			
EFFECTIVE	38.0(258)	82.9(570)	59	75	167	195																																																																																			
Mechanical properties tested in state of delivery																																																																																									
US - testing		yes	Results: SEP 1921,group 3/class Cc - OK ASTM A-388 FBH 1/5inch (5.08 mm)										Manufacturer: PJSC DNIPROSPETSSTAL Date: 19.04.12 Manager of quality assurance department - V. Kapaieva Signed:																																																																												
Radiation free; mercury free. No Weld or Weld repair.																																																																																									
Zaporozhye Made in Ukraine.																																																																																									

