



HT# A05798

C212985

1382

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№8367/PO43227 DIN EN 10088-3-05, DIN EN 10272-08, DIN EN 10222-5-00, ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond. A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10 GR B8M, CL 1; ASME SA-193/SA-193M-10 GR B8, CL 1; ASTM A320/A320M-08 GR B8M, CL 1; ASME SA-320/SA-320M-10 GR B8, CL 1; NACE MR 0175-03; NACE MR 0103-10										Sheets: 6 Sheet: 5 INSPECTION CERTIFICATE EN10204/3.1 Nr.332059 PLANT ORDER № 8014908367																						
	 GMS Certified		CUSTOMER DSS INTERNATIONAL SA Switzerland										PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel forged, peeled. Прутки из коррозионноустойчивых (нержавеющих) сталей кованые, обточенные. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 18.750in/476.25 mm L=10.295 ft/3.140m Grade: 316/316L/1.4401/1.4404		QUANTITY: (number of pcs) 1bund Q-10022 lb/4546 kg																		
ANALYSIS, %																																	
	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B															
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10																	
CAST	.019	.40	1.43	.038	.023	16,90	10.25	2.05	.072	.33	.05	.08	.005	.11	.01	.027	.0095	.0022															
№ A05798																																	
DIN EN 10002-1, ASTM A370-09																																	
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation A5 % L Q In 2 inches (50mm) or 4D, min, % L		Reducti on of area, Z % L	Brinell Hardness HB	Impact strength, KV, J L Q																									
	REQUIRED	205	240	515-690	45 35	40	50	140-217	100	60																							
	EFFECTIVE	278	298	554	59 48	58	73	163	191 191 191	65 65 65																							
Mechanical properties tested in state of delivery										TECHNICAL REQUIREMENTS: Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) <table border="1"> <tr> <td>A</td> <td>B</td> <td>C</td> <td>D</td> </tr> <tr> <td>thin</td> <td>thick</td> <td>thin</td> <td>thick</td> </tr> <tr> <td>2.0</td> <td>1.5</td> <td>2.0</td> <td>1.0</td> </tr> <tr> <td>0.0</td> <td>0.0</td> <td>0.0</td> <td>1.0</td> </tr> </table> ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа								A	B	C	D	thin	thick	thin	thick	2.0	1.5	2.0	1.0	0.0	0.0	0.0	1.0
A	B	C	D																														
thin	thick	thin	thick																														
2.0	1.5	2.0	1.0																														
0.0	0.0	0.0	1.0																														
US - testing		yes	Results: ASTM A388/A388M-FBH1/5"; EN 10228-4 type 1a; class 3:OK																														
Radiation free; mercury free. No Weld or Weld repair.										Manufacturer: PrJSC DNIPROSPETSSTAL Date: 30.03.18 Manager of quality assurance department - V. Kapaieva Signed: Zaporozhye Made in Ukraine.																							

