

HTA A05798 SWA 4961

CA12985

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

Contract No.: 20002
 TECHN. PROTOCOL № 390-11 SPEC. № 8367/PO43227
 DIN EN 10088-3-05, DIN EN 10272-08, DIN EN 10222-5-00, ASTM A182/A182M-10, ASME SA-182/SA-182M-10, ASTM A276-10, ASTM A314-08, ASTM A479/A479M-10, ASME SA-479/SA-479M-10, ASTM A484/A484M-10, AMS-QQ-S-763B-06
 Cond. A, AMS 5648K-07, AMS 5653F-07, ASTM A193/A193M-10GR B8M, CL1, ASME SA-193/SA-193M-10 GR B8, CL 1, ASTM A320/A320M-08 GR B8M, CL 1, ASME SA-320/SA-320M-10 GR B8, CL 1, NACE MR 0175-03, NACE MR 0103-10

CUSTOMER
DSS INTERNATIONAL
 SA Switzerland

PRODUCT DESCRIPTION
 Bars and rods of corrosion-resistant (stainless) steel forged, peeled, Prutki из коррозионностойких (нержавеющих) сталей кованные, обточенные.
STEEL MAKING PROCESS: EAF+AOD
СПОСОБ ВЫПЛАВКИ: Электроплавочная печь + АКР
 Round 18.750; m/476.25 mm L=10.295 ft/3.140m
Grade: 316/316L/1.4401/1.4404

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1.00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A05798	.019	.40	1.43	.038	.023	16.90	10.25	2.05	.072	.33	.05	.08	.005	.11	.01	.027	.0095	.0022

DIN EN 10002-1, ASTM A370-09

MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%	Tensile Strength, Rm, (N/mm ²)	Elongation		Reducti on of area, Z %	Brinell Hardness HB	Impact strength, KV, J		
			A ₅ %	In 2 inches (50mm) or 4D, min, %			L	L	Q
REQUIRED	205	515-690	45	35	50	140-217	100	60	
EFFECTIVE	278	554	59	48	73	163	191	191	65 65 65

TECHNICAL REQUIREMENTS:
 Macrostructure – GOOD
 GRAIN SIZE : 5 to ASTM E 112-96(2004)
 Nonmetallic inclusions ASTM E 45-05 (Method A)
 A B C D
 thin thick thin thick thin thick thin thick
 2.0 1.5 2.0 1.0 0.0 0.0 1.0 1.0 1.0
 ICC-ASTM A262-08 (practice E)-test: O.K.
 Dimension/surface defects test, anti-mixing test – OK
 We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа

Manufacturer: PrJSC DNIPROSPETSSTAL
 Date: 30.03.18 Manager of quality assurance department - V. Kapateva
 Signed: 
 Zaporozhye
 Made in Ukraine.

125

Radiation free; mercury free. No Weld or Weld repair.

US - testing yes Results: ASTM A388/A388M-FBH1/5"; EN 10228-4 type Ia; class 3-OK

Mechanical properties tested in state of delivery