C224524

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

Contract №.: 20002
TECHN.PROTOCOL № 390-11 SPEC.№ 0111/PO44618
DIN EN 10088-3-05,DIN EN 10272-08,DIN EN 10222-5-00,ASTM A182/A182M-10;ASME SA-182/SA-182M-10;ASTM A276-10;ASTM A314-08;ASTM A479/A479M-10;ASME SA-479/SA-479M-10;ASTM A484/A484M-10;AMS-QQ-S-763B-06 Cond.A;AMS 5648K-07;AMS 5653F-07;ASTM A193/A193M-10GR B8M,CL.1; ASME SA-193/SA-193M-10 GR B8,CL.1 ;ASTM A320/A320M-08 GR B8M,CL.1;ASME SA-320/SA-320M-10 GR B8,CL.1;NACE MR 0175-03;NACE MR 0103-10

Sheets:4 **Sheet: 4**
INSPECTION CERTIFICATE EN10204/3.1 **Nr.336960**
PLANT ORDER № 8014900111

QMS Certified

CUSTOMER
DSS INTERNATIONAL
SA Switzerland

PRODUCT DESCRIPTION
Bars and rods of corrosion-resistant (stainless) steel forged, peeled.Прутки из коррозионностойких (нержавеющих) сталей кованые, обточенные.
STEEL MAKING PROCESS: EAF+AOD
СПОСОБ ВЫПЛАВКИ:Электродуговая печь+АКР
Round 15.000in/381.00 mm L= 8.115 ft/2.475 m;
Grade: 316/316L/1.4401/1.4404

QUANTITY: **1bund ●-5057 lb/2294 kg**
(number of pcs)

Delivery condition
solution annealed :1940° F(1060°C)water 30minutes
термообработка:закалка в воду

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00--13.00	2.00--2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A06284	.018	.45	1.29	.040	.025	16,78	10.30	2.06	.076	.33	.05	.07	.005	.12	.011	.028	.011	.0022

DIN EN 10002-1,ASTM A370-09

MECHANICAL PROPERTIES	Yield Strength, (N/mm^2) R0.2%	R 1.0%	Tensile Strength, Rm, (N/mm^2)	Elongation A, % L ●	In 2 inches (50mm) or 4D,min,% L	Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J L	●
REQUIRED	205	240	515-690	45 35	40	50	140-217	100	60
EFFECTIVE	279	304	549	58 48	57	73	163	190 190 190	66 66 66

Mechanical properties tested in state of delivery

US - testing	yes	Results: ASTM A388/A388M-FBHI/5";EN 10228-4 type 1a;class 3:OK

Radiation free; mercury free. No Weld or Weld repair.

TECHNICAL REQUIREMENTS:
Macrostructure – GOOD
GRAIN SIZE : 5 to ASTM E 112-96(2004)
Nonmetallic inclusions ASTM E 45-05 (Method A)

A		B		C		D	
thin	thick	thin	thick	thin	thick	thin	thick
3.0	2.0	2.0	1.0	0.0	0.0	1.0	1.0

ICC-ASTM A262-08 (practice E)-test: O.K.
Dimension/surface defects test, anti-mixing test – OK
We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа
Ratio of reduction-6.3:1

Manufacturer:PrJSC DNIPROSPETSSTAL
Date: 16.08.18 **Manager of quality assurance department** - V. Kapaieva
Signed:
Zaporozhye
Made in Ukraine.

AVS