



C220881


PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№ 9728/P044311 DIN EN 10088-3-05, DIN EN 10272-08, DIN EN 10222-5-00, ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10GR B8M,CL1; ASME SA-193/SA-193M-10 GR B8,CL 1 ;ASTM A320/A320M-08 GR B8M,CL 1; ASME SA-320/SA-320M-10 GR B8,CL1; NACE MR 0175-03; NACE MR 0103-10	Sheets:7 Sheet: 5 INSPECTION CERTIFICATE EN10204/3.1 Nr.335735 PLANT ORDER № 8014909728
---	---	---

 GMS Certified	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel forged, peeled. Прутки из коррозионностойких (нержавеющих) сталей кованные, обточенные. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+AKP Round 15.000in/381.00 mm L= 8.393 ft/2.56 m Grade: 316/316L/1.4401/1.4404	QUANTITY: 1bund Q-5243 lb/2378 kg (number of pcs)
			Delivery condition solution annealed :1940 ⁰ F(1060 ⁰ C)water 30minutes термообработка:закалка в воду

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A06143	.018	.48	1.42	.040	.026	16,71	10.20	2.08	.075	.29	.05	.08	.009	.11	.015	.028	.013	.0022

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS:									
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J		Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 3.0 2.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа Ratio of reduction-5.6:1									
	REQUIRED	205		240	45 35			40	50										
EFFECTIVE	280	301	580	61 54	59	75	170	190 190 190	64 64 64										
Mechanical properties tested in state of delivery																			

US - testing	yes	Results: ASTM A388/A388M-FBH1/5"; EN 10228-4 type 1a; class 3:OK	Manufacturer: PrJSC DNIPROSPETSSTAL Date: 10.07.18 Manager of quality assurance department - V. Kapaieva Signed:  Zaporozhye Made in Ukraine.
Radiation free; mercury free. No Weld or Weld repair.			

ANS