



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.i.
 Telefono 0444.968211 - Fax 0444.963836
 Stab. - 39100 BOLZANO (Italia) - Via A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: **EN 10204 (2004), 3.1 / ISO 10474 (2013), 3.1**
 Nach/According to/Seion

Certificato nr. **MEST416061 / 2019 /**
 Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
VALBRUNA CANADA LTD
8724 HOLGATE CRESCENT
L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura : **Forged - Annealed Peeled**
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore :
 Hersteller/Item/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: **903007423**
 Bestell
 Your order
 Commande

Tipo di Elaborazione **E+AOD**
 Erhmelzungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Conferma ordine nr: **EI19002789**
 Werks/Our Order/Ref. nr.

Qualità: **316/316L**
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'assesseur

MR

Avviso di Spedizione: **D-VI19015576**
 Lieferanzeige/Packing list/B.L.

Marca: **APML**
 Markenbezeichnung
 Brand / Nuance

Punzonatura: **316/316L**
 Kennzeichnung
 Marking
 Marquage

SPECIFICHE :	Note
Anforderungen / Requirements / Exigences	Aufzeichnungen / Notes / Notes
VSI 0.316/316L A	
AISI 316/316L	
AMS 5648 M S31600 A	
AMS 5653 H S31603 A	
AMS-QQ-S-763 D 316/316L A	
ASME SA182 2017 S31600/03 A (0)	(0)Section II Part A 2017 EDITION For products machined directly from bar refer to ASME SA479.
ASME SA193 2017 B8M CLASS 1 (1)	(1)Section II Part A 2017 EDITION
ASME SA276 2017 S31600/03 A (2)	(2)Section II Part A 2017 EDITION
ASME SA320 2017 B8M CLASS 1 (3)	(3)Section II Part A 2017 EDITION
ASME SA479 2017 S31600/03 A (4)	(4)Section II Part A 2017 EDITION
ASTM A182 2018 S31600/03 A (5)	(5)For products machined directly from bar refer also to ASTM A479.
ASTM A193 2017 B8M CLASS 1	
ASTM A262 2015 PRACTICE E	
ASTM A276 2017 S31600/03 A	
ASTM A314 2015 S31600/03	
ASTM A320 2017A B8M CLASS1	
ASTM A370 2017 .	
ASTM A473 2001 S31600/03 (6)	(6)Chemical analysis only.
ASTM A479 2018 S31600/03 A	
MIL-S-862 B/1 316/316L	
NACE MR0103 2015 S31600/03 A (7)	(7)ANSI/NACE MR0103/ISO 17945 November 23, 2015
NACE MR0175 2015 S31600/03 A (8)	(8)ANSI/NACE MR0175/ISO 15156-3, third edition November 23,2015
QQ-S-763 F 316/316L A	

Tolleranza: ASTM A484-18A TABLE 3

Pos. nr. Pos. nr. Item nr. Nr. de poste	Oggetto Gegenstand Product description Descript. du produit	Tolleranza/Allowance/Tolerance					
		Dimensioni - In Abmessungen Dimension Dimension	Lunghezza - In Länge Length Longueur	Colata Schmelze Heat Coulée	Pezzi Stückzahl Pieces Pièces	Peso - LB Gewicht Weight Poids	Lotto nr. Lotnr. Lot nr. Lotti
0010	Round	13,0000	142/ 142	279662		5.540	835403640

ANS

Vicenza, 29/05/19 VCC008 - MEST416061	Il collaudatore di stabilimento der Werkssachverständige / Works Inspector / L'agent d'usine M. RIZZOTTO	Direzione Qualità Qualitätsmanagement/Quality Management/Gestion Qualité R. BERTELLI	Direzione Prodotto Produktmanagement/Product Management/Direction Produit P. MESSORI	Pagina 1 di 3
--	---	---	---	------------------



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.i.
 Telefono 0444.968211 - Fax 0444.963836
 Stab.: 39100 BOLZANO (Italia) - Via A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: EN 10204 (2004) 3.1 / ISO 10474 (2013) 3.1
 Nach/According to/Señal

Certificato nr. MEST416061 / 2019 /
 Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
VALBRUNA CANADA LTD
 8724 HOLTGATE CRESCENT
 L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura: Forged - Annealed Peeled
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore:
 Hersteller/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: 903007423
 Bestell
 Your order
 Commande

Tipo di Elaborazione: E+A0D
 Erschließungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Signes de l'usine productrice



Conferma ordine nr: EI19002789
 Werk/Dat. Order/Ref. nr.

Qualità: 316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Fonction de l'essayeur

MR

Avviso di Spedizione: D-VI19015576
 Lieferanzeige/Packing list/B.L.

Marca: APML
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 316/316L
 Kennzeichnung
 Marking
 Marquege

TEST ALLO STATO DI FORNITURA													
Test on delivery condition / Prüfung auf lieferbarem produkt / Test a l'état de fourniture / Prueba sobre el material así como entregado													
TEST	Provetta / Probe Specimen/Éprouvette Larg. Diam. Spess. Width Diam. Thickness Larg. diam. épais. mm.	Posiz. Saggio Probenlage Lage der Éprouvette	1) L=longitudinale/längs, T=trasversale/quer, Q=Tangenziale/tangentia.		Snervamento Streckgrenze Yield Stress Limite élastique Rp 0,2% N.S.I.	Snervamento Streckgrenze Yield Stress Limite élastique	Resistenza Zugfestigkeit Tensile strength Résistance à traction Rm N.S.I.	Allungamento Brüderung Élongation Allongement E 4d %		Strizione Emweichung Reduction of area Striction RA %	Resilienza Kerbschlagarbeit Impact Value Resilience	Durezza Härte Hardness Dureté HB	
			min	max				min	max				
A	12,5	68	L		30	-	75	-	40	-	50	-	140
					40		81		57		73		223
													169

TEST ALLO STATO DI FORNITURA		
Test on delivery condition / Prüfung auf lieferbarem produkt / Test a l'état de fourniture / Prueba sobre el material así como entregado		
TEST	min	max
A Grain size for ASTM E112		1

Mechanical properties according to ASTM A370.

Analisi chimica												
Chemische Zusammensetzung/Chemical Analysis/Analyse chimique												
Colata / Heat	min	max	1,25	16,50	2,00	10,00	14,00	0,040	0,030	0,100		
Schmelze/Coulee	0,030	1,00	2,00	18,00	3,00	1,00	14,00					
	C %	Si %	Mn %	Cr %	Mo %	Cu %	Ni %	Co %	P %	S %	N %	
279662	0,016	0,38	1,75	16,77	2,02	0,51	10,00	0,102	0,029	0,025	0,089	

Corrosion test in 16% sulfuric acid and copper sulfate solutions							
Test standard: ASTM A262-Practice E							
Test	Heat treatment before test	Length of Period (h)	Test temp (°C)	Bend Angle (°)	Ø spindle (mm)	Result of visual inspection at 20 x magnification after bend test	Result
Intergranular corrosion	Sensitization	15	boil	180	5	Absence of cracks	SATISFACTORY

Produced without class I-II Ozone depleting substances.
 Solution heat treated free from continuous carbide network.
 Micro and macro etch test : OK
 Reduction ratio = 4,7 : 1
 Annealing temperature : 1940° F for 6 h/water.
 Material is DFARS Compliant

Sono state soddisfatte tutte le condizioni richieste
 Die ges.ellen Anforderungen sind erfüllt
 The material has been furnished in accordance with the requirements
 Le matériel a été trouvé conforme aux exigences

Controllo antimiscelazione: OK
 Verwechslungsprüfung: spectralanalytisch durchgeführt
 Antimixing test performed OK
 Contrôle antimélange fait: r a s

Controllo visivo e dimensionale: soddisfa le esigenze
 Beschäftigung und Ausmessung: ohne Beanstandung
 Visual inspection and dimensional checks satisfactory
 Contrôle visuel et dimensionnel satisfaisant

Melted and manufactured in Italy No welding or weld repair Material free from Mercury contamination
 We declare that the finished product is checked for radioactive contamination through Portal System when it leaves the production plant.

Vicenza, 29/05/19 VCQ008 - MEST416061	Il collaudatore di stabilimento der Werkssachverständige / Works Inspector / Usine Client M. RIZZOTTO	Direzione Qualità Qualitätsmanagement/Quality Management/Gestion Qualité R. BERTELEI	Direzione Prodotto Produktmanagement/Product Management/Direction Produit P. MESSORI	Pagina 2 di 3
--	--	---	---	------------------



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.1
 Telefono 0444.968211 - Fax 0444.963836
 Stab.: 39100 BOLZANO (Italia) - Via A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: EN 10204 (2004), 3.1 / ISO 10474 (2013), 3.1

Certificato nr. MEST416061 / 2019 /
 Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
 VALBRUNA CANADA LTD
 8724 HOLGATE CRESCENT
 L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura: Forged - Annealed Peeled
 Lieferzustand
 Delivery state
 Etai de livraison

Produttore:
 Hersteller/Werk/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: 903007423
 Bestell
 Your order
 Commande

Tipo di Elaborazione: E+AOD
 Ershmelzungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Conferma ordine nr: EI19002789
 Werks/Our Order/Ref n:

Qualità: 316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'essayeur

NR

Avviso di Spedizione: D-VI19015576
 Referanzsign/Packing list/B.L.

Marca: APM.L
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 316/316L
 Kennzeichnung
 Marking
 Marquage

QUALITY MANAGEMENT SYSTEM CERTIFIED BY LLOYD'S REGISTER ACCORDING TO ISO 9001 : 2015, IATF 16949 : 2016, AS 9100D

The Quality Management System is Certified acc. Pressure Equipment Directive 2014/68/EU Annex 1, chapt.4.3 by TUEV and LLOYD'S
 Any act of tampering, modification, alteration, counterfeiting and/or falsification and/or any other action which modifies the contents of this test certificate shall constitute a violation of applicable civil and criminal laws. Acciaierie Valbruna shall protect its rights and interests before any competent court, authority and jurisdiction.
 Maximal and/or Valplus grades/products are manufactured with ladle techniques to control composition, distribution, size and shape of non-metallic inclusions for improved machinability.
 The supplied product conforms to requirements expressly requested by the purchaser and conforms to requirements specified by certified norms and standards. Should the product be used for more severe, critical and/ or in any case different applications than those the material is generally intended for, any different and/or supplementary requirements shall be specifically demanded, at least upon order of the Product by the Purchaser. Acciaierie Valbruna SpA shall not be responsible for any improper use of the Products.

Vicenza, 29/05/19 VCQC08 - MEST416061	Il collaudatore di stabilimento der Werkssachverständige / Works Inspector / L'agent d'usine M. RIZZOTTO	Direzione Qualità Qualitätsmanagement/Quality Management/Gestion Qualité R. BERTELLI	Direzione Prodotto Produktmanagement/Product Management/Direction-Produit P. MESSORI	Pagina 3 di 3
---	---	---	---	------------------