



C231846


PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№0549/PO44837 DIN EN 10088-3-05, DIN EN 10272-08, DIN EN 10222-5-00; ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A: AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10 GR B8M, CL1; ASME SA-193/SA-193M-10 GR B8, CL 1; ASTM A320/A320M-08 GR B8M, CL 1; ASME SA-320/SA-320M-10 GR B8, CL1; NACE MR 0175-03; NACE MR 0103-10	Sheets:4 Sheet: 4 INSPECTION CERTIFICATE EN10204/3.1 Nr.339863 PLANT ORDER № 8014900549
---	--	---

 QMS Certified	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel forged, peeled. Прутки из коррозионностойких (нержавеющих) сталей кованные, обточенные. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь-АКР Round 18.750in/476.25 mm L=10.689 ft/3.260m Grade: 316/316L/1.4401/1.4404	QUANTITY: (number of pcs) 1bund Q-10626 lb/4820 kg Delivery condition solution annealed :1922° F(1050° C)water 36minutes термообработка:закалка в воду
--	--	--	---

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A06586	.021	.43	1.31	.037	.026	17.00	10.36	2.13	.078	.27	.05	.05	.005	.10	.01	.023	.009	.0018

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS: Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 3.0 2.0 3.0 2.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа Ratio of reduction-7.4:1									
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N /mm ²)	Elongation		Reduction of area, Z %	Brinell Hardness HIB	Impact strength, KV, J											
				A ₅ %	In 2 inches (50mm) or 4D, min, %			L	Q										
REQUIRED	205	240	515-690	45 35	40	50	140-223	100	60										
EFFECTIVE	283	323	581	60 53	59	79	170	197 197 197	67 67 67										

US - testing	yes	Results: ASTM A388(A388M)-FBH1/5"; EN 10228-1 type Ia; class 3:OK	Manufacturer: PrJSC DNIPROSPETSSTAL Date: 15.11.18 Manager of quality assurance department - V. Kapaieva Signed: Zaporozhye Made in Ukraine.
Radiation free; mercury free. No Weld or Weld repair.			

ANS