




61 C229099


PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№0111/PO44618 DIN EN 10088-3-05, DIN EN 10272-08, AD2000-Merkblatt W2; AD 2000-Merkblatt W10; ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10GR B8M, CL1; ASME SA-193/SA-193M-10 GR B8, CL 1; ASTM A320/A320M-08 GR B8M, CL 1; ASME SA-320/SA-320M-10 GR B8, CL1; NACE MR 0175-03; NACE MR 0103-10										Sheets:4 Sheet: 1 INSPECTION CERTIFICATE EN10204/3.1 Nr.337468 PLANT ORDER № 8014900111
	 CUSTOMER DSS INTERNATIONAL SA Switzerland										QUANTITY: (number of pcs) 1bund Q-4048 lb/1836 kg

 GMS Certified	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line. Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, отбоченные на линии Ландграф. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 6.250in/158.75 mm L=5.640m/18.492ft Grade: 316/316L/1.4401/1.4404										Delivery condition solution annealed :1900°F(1040°C)water 30minutes термообработка:закалка в воду
---	--	--	--	--	--	--	--	--	--	--	---

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1.00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A06341	.020	.43	1.29	.040	.027	16.87	10.20	2.03	.064	.29	.05	.06	.005	.12	.01	.026	.0108	.0025

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS:												
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z% L	Brinell Hardness HB	Impact strength, KV, J		Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 2.5 1.5 1.5 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order Ratio of reduction-15.1:1												
	L	Q		In 2 inches (50mm) or 4D, min, % L	L			L	L											Q		
REQUIRED	205	240	515-690	45	-	40	50	140-217	100	-												
EFFECTIVE	280	317	563	62	-	57	77	167	230	230	230	-										
	282	329	567	61	-	57	77	167	226	226	226	-										

Mechanical properties tested in state of delivery										Manufacturer: PrJSC DNIPROSPETSSTAL Date: 31.08.18 Manager of quality assurance department - V. Kapaieva Signed:  Zaporozhye Made in Ukraine.									
US - testing		yes	Results: ASTM A388/A388M-FBH1/8"; EN 10308 type 1a; class 3:OK																
Radiation free; mercury free. No Weld or Weld repair.																			

Fe09/20

ANS