18 pcs C241970

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

Contract No.: 20002
TECHN.PROTOCOL № 390-11 SPEC.№ 2425/PO45729
DIN EN 10088-3-05,DIN EN 10272-08,AD2000-Merkblatt W2;AD 2000-Merkblatt W10;ASTM A182/A182M-10;ASME SA-182/SA-182M-10;ASTM A276-10;ASTM A314-08,ASTM A479/A479M-10;ASME SA-479/SA-479M-10;ASTM A484/A484M-10;AMS-QQ-S-763B-06 Cond.A;AMS 5648K-07;AMS 5653F-07;ASTM A193/A193M-10GR B8M,CL1; ASME SA-193/SA-193M-10 GR B8,CL 1 ;ASTM A320/A320M-08 GR B8M,CL 1;ASME SA-320/SA-320M-10 GR B8,CL1;NACE MR 0175-03;NACE MR 0103-10

Sheets:3 **Sheet: 1**
INSPECTION CERTIFICATE EN10204/3.1 **Nr. 344970**
PLANT ORDER № 8014902425

QMS Certified

CUSTOMER
DSS INTERNATIONAL SA Switzerland

PRODUCT DESCRIPTION
Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line.Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, обточенные на линии Ландграф.
STEEL MAKING PROCESS: EAF+AOD
СПОСОБ ВЫПЛАВКИ:Электродуговая печь+АКР
Round 6.250in/158.75 mm L=5.620/18.426ft L=5.620m/18.426ft
Grade: 316/316L/1.4401/1.4404

QUANTITY: **1bund Q-4030 lb/1828 kg**
(number of pcs) **1bund Q-2015 lb/914 kg**

Delivery condition
solution annealed :1900^{0}F(1040^{0}C)water 30minutes
термообработка:закалка в воду

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1.00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00--13.00	2.00--2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A07179	.020	.47	1.46	.040	.022	16.83	10.40	2.08	.075	.25	.04	.07	.007	.08	.022	.025	.008	.0023

DIN EN 10002-1,ASTM A370-09

MECHANICAL PROPERTIES	Yield Strength, (N/mm^2) R0.2% R 1.0%		Tensile Strength, Rm, (N /mm^2)	Elongation A$_5$% L Q	Elongation In 2 inches (50mm) or 4D,min,% L	Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J L	Impact strength, KV, J Q
REQUIRED	205	240	515-690	40 -	40	50	140-217	100	-
EFFECTIVE	299 302	344 347	557 553	60 - 60 -	58 58	78 80	163 163	202 202 202 206 206 206	-

Mechanical properties tested in state of delivery

US - testing	yes	Results: ASTM A388/A388M-FBH1/8",EN 10308 type 1a;class 3:OK

Radiation free; mercury free. No Weld or Weld repair.

TECHNICAL REQUIREMENTS:
Macrostructure – GOOD
GRAIN SIZE : 5 to ASTM E 112-96(2004)
Nonmetallic inclusions ASTM E 45-05 (Method A)

A		B		C		D	
thin	thick	thin	thick	thin	thick	thin	thick
2.5	2.0	2.0	2.0	0.0	0.0	1.0	1.0

ICC-ASTM A262-08 (practice E)-test: O.K.
Dimension/surface defects test, anti-mixing test – OK
We acknowledge that the delivered products conform to the requirements of the order
Ratio of reduction-15.1:1

Manufacturer:PrJSC DNIPROSPETSSTAL
Date: 29.04.19 **Manager of quality assurance department** - V. Kapaieva
Signed:
Zaporozhye
Made in Ukraine.

Mar 02/20

AVS