



C275675
11029

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	<p>Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№ 8919/PO49148 DIN EN 10088-3-05, DIN EN 10272-08, AD2000-Merkblatt W2; AD 2000-Merkblatt W10; ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10GR B8M, CL1 (EXC PAR 7.2); ASME SA-193/SA-193M-10 GR B8, CL 1 (EXC PAR 7.3); NACE MR 0175-03; NACE MR 0103-10</p>	<p>INSPECTION CERTIFICATE EN10204/3.1 Nr. 360062 PLANT ORDER № 8014908919</p>	
 GMS Certified	<p>CUSTOMER DSS INTERNATIONAL SA Switzerland</p>	<p>PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line. Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, обточенные на линии Ландграф. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 3.750in/95.25 mm L=5.600/18.361ft L=5.620m/18.426ft L=5.360/17.574ft Grade: 316/316L/1.4401/1.4404</p>	<p>QUANTITY: (number of pcs) 1bund Q-2870 lb/1302kg 1bund Q-3593 lb/1630kg 1bund Q-688 lb/312kg</p> <p>Delivery condition solution annealed :1900°F(1040°C)water 30minutes термообработка:закалка в воду</p>

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1.00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<10	<.40	<10	<.20	<.15	<.40	<.20	<.10		
CAST № A08835	.020	.52	1.36	.040	.024	16.70	10.22	2.06	.073	.30	.05	.05	.005	.11	.01	.030	.009	.0023

DIN EN 10002-1, ASTM A370-09


MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J	
	L	Q		A ₅ % L	In 2 inches (50mm) or 4D, min, % L			L	Q
REQUIRED	205	240	515-690	40 -	40	50	140-217	100	-
EFFECTIVE	293 294	327 328	566 568	60 - 60 -	59 59	79 79	167 167	218 218 218 215 215 215	-

TECHNICAL REQUIREMENTS:
Macrostructure – GOOD
GRAIN SIZE : 5 to ASTM E 112-96(2004)
Nonmetallic inclusions ASTM E 45-05 (Method A)
A B C D
thin thick thin thick thin thick thin thick
2.5 2.0 2.0 2.0 0.0 0.0 1.0 1.0
ICC-ASTM A262-08 (practice E)-test: O.K.
Dimension/surface defects test, anti-mixing test – OK
We acknowledge that the delivered products conform to the requirements of the order
Ratio of reduction-35.1:1

Mechanical properties tested in state of delivery

US - testing	yes	Results: ASTM A388/A388M-FBH1/8"; EN 10308 type 1a; class 3:OK
--------------	-----	--

Date: 14.08.2020 **Manager of quality assurance**
department - V. Kapaieva Signed:
Zaporozhye
Melted and Produced in Ukraine.
MELTED and MANUFACTURED
PrJSC " Dnipropetsstal"
Phone number +380612834255
e-mail: info@dss.com.ua
http://www.dss-ua.com



Radiation free; mercury free. No Weld or Weld repair.

INS