


C277649

1738


PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№9684/PO49596 DIN EN 10088-3-05, DIN EN 10272-08, DIN EN 10222-5-00; ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10GR B8M, CL1; ASME SA-193/SA-193M-10 GR B8, CL 1; ASTM A320/A320M-08 GR B8M, CL 1; ASME SA-320/SA-320M-10 GR B8, CL1; NACE MR 0175-03; NACE MR 0103-10	INSPECTION CERTIFICATE EN10204/3.1 Nr.363163 PLANT ORDER № 8014909684
---	---	--

	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel forged, peeled. Прутки из коррозионностойких (нержавеющих) сталей кованные, обточенные. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 13.000in/330.20 mm L=10.230 ft/3.120m L=8.738 ft/2.665m Grade: 316/316L/1.4401/1.4404	QUANTITY: 1bund Q-4802 lb/2178 kg (number of pcs) 1bund Q-4136 lb/1876 kg Delivery condition solution annealed :1940 ⁰ F(1060 ⁰ C)water 30minutes термообработка:закалка в воду
---	--	--	---

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A09131	.020	.43	1.30	.037	.025	17.06	10.15	2.08	.07	.27	.05	.06	.005	.13	.011	.030	.0095	.0022

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS:																			
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J		Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 2.5 2.0 2.0 2.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order/Подтверждаем, что поставленная продукция соответствует требованиям заказа Ratio of reduction-6.1:1																			
	L	Q		In 2 inches (50mm) or 4D,min,% L	L			Q																					
REQUIRED	205	240	515-690	45 35	40	50	140-217	100	60																				
EFFECTIVE	280	304	576	61 55	58	74	170	197 197 197	65 65 65																				

Mechanical properties tested in state of delivery			Date: 06.11.2020 Manager of quality assurance department - V. Kapaieva Signed: 		
US - testing	yes	Results: ASTM A388/A388M-FBH1/5"; EN 10228-4 type 1a; class 3:OK	Melted and Produced in Ukraine. MELTED and MANUFACTURED PrJSC " Dniprospeetsstal" Phone number +380612834255 e-mail: info@dss.com.ua http://www.dss-ua.com		
Radiation free; mercury free. No Weld or Weld repair.					

INS