

C193765



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.i.
 Telefono 0444.968211 - Fax 0444.963836
 Stab.: 39100 BOLZANO (Italia) - Via a.A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: EN 10204 (2004), 3.1 / ISO 10474 (2013), 3.1

Certificato nr. MEST115628 / 2017 /
 Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
 VALBRUNA CANADA LTD
 8724 HOLLGATE CRESCENT
 L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura: Forged - Annealed FORGED
 Liefeszustand
 Delivery state
 Etat de livraison

Produttore:
 Hersteller/Werks/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: 705006370 Stock - Canada

Bestell
 Your order
 Commande

Tipò di Elaborazione: E+AOD
 Erweichungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Conferma ordine nr: EI17005543

Werkel/Our Order/Ref.nr.

Qualità: 316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'essayeur

MR

Avviso di Spedizione: D-VI17023377
 Lieferanzeige/Packing list/B.L.

Marca: APML
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 316/316L
 Kennzeichnung
 Marking
 Marquage

SPECIFICHE :

Anforderungen / Requirements / Exigences

Note:

Anzeichnungen / Notes / Notes

VSI 0 316/316L A
 AISI 316/316L
 AMS 5648 M S31600 A
 AMS 5653 H S31603 A
 AMS-QQ-S-763 D 316/316L A
 ASME SA182 2015 S31600/03 A (0)
 ASME SA193 2015 B8M CLASS1 (1)
 ASME SA276 2015 S31600/03 A (2)
 ASME SA320 2015 B8M CLASS1 (3)
 ASME SA479 2015 S31600/03 A (4)
 ASTM A182 2016 S31600/03 A (5)
 ASTM A193 2016 B8M CLASS1
 ASTM A262 2015 PRACTICE E
 ASTM A276 2017 S31600/03 A
 ASTM A314 2015 S31600/03
 ASTM A320 2017A B8M CLASS1
 ASTM A370 2017
 ASTM A473 2001 S31600/03 (6)
 ASTM A479 2017 S31600/03 A
 MIL-S-862 B/1 316/316L
 NACE MR0103 2010 S31600/03 A
 NACE MR0175 2015 S31600/03 A (7)
 QQ-S-763 F 316/316L A

(0)SECTION II PT.A 2015 EDITION For products machined directly from bar refer to ASME SA479.

(1)SECTION II PT.A 2015 EDITION

(2)SECTION II PT.A 2015 EDITION

(3)SECTION II PT.A 2015 EDITION

(4)SECTION II PT.A 2015 EDITION

(5)For products machined directly from bar refer also to ASTM A479.

(6)Chemical analysis only.

(7)ANSI/NACE MR0175/ISO 15156-3, third edition November 23,2015

Tolleranza: ASTM A484-18 TABLE 3

Tolerance/Allowance/Tolerance

Pos. nr. Pos. nr. Num. nr. Nr. de poste	Oggetto Objet/Objekt Product description Descrip. du produit	Dimensioni - In Abmessungen Dimension Dimension	Lunghezza - In Länge Length Longueur	Colata Schmelze Heat Coulée	Pezzi Stückzahl Pieces Pièces	Peso - LB Gewicht Weight Poids	Lotto nr. Lotnr. Lot nr. Lot nr.
0040	Round	8,5000	233/ 233	273944		3.911	711613350

Vicenza, 28/08/17

VCQ008 - MEST115628

Il collaudatore di stabilimento / der Werkssachverständige / Works inspector / L'agent d'usine

M. RIZZOTTO *[Signature]*

Pagina - 1 di 3

ANS



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.i.
 Telefono 0444.968211 - Fax 0444.963836
 Stab.: 39100 BOLZANO (Italia) - Via A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

C193765

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: EN 10204 (2004), 3.1 / ISO 10474 (2013), 3.1

Certificato nr. MEST115628 / 2017 /

Nach/According to/Belon

Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
VALBRUNA CANADA LTD
 8724 HOLGATE CRESCENT
 L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura: Forged - Annealed FORGED
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore:
 Hersteller/Item/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: 705006370 Stock - Canada
 Bestell
 Your order
 Commande

Tipo di Elaborazione: E+AOD
 Erweichungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Confirma ordine nr: EI17005543
 Werks/Our Order/Ref nr.

Qualità: 316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'essayeur

MR

Avviso di Spedizione: D-VI17023377
 Lieferanzeige/Packing list/B.L.

Marca: APML
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 316/316L
 Kennzeichnung
 Marking
 Marquage

TEST ALLO STATO DI FORNITURA												
Test on delivery condition / Prüfung auf lieferbarem produkt / test a l'etat de fourniture / Prueba sobre el material así como entregado												
1) L-Longitudinale/Along, T-Transversale/Quer, Q-Tangenziale/Tangential												
TEST	Provetta/ Probe Specimen/Eprouvette Larg. diam. Spess. Brelle Diam. Dicke Width Diam. Thickness Larg. diam. epess. mm	°F	Posiz. Saggio Position Location Emplacement	Snervamento Streckgrenze Yield Stress Limite élastique Rp 0,2% k.s.t.	Snervamento Streckgrenze Yield Stress Limite élastique	Resistenza Zugfestigkeit Tensile strength Résistance à traction Rm k.s.t.	Allungamento Bruchdehnung Elongation Allongement E 4d %	Strizione Einseitige Reduction of area Striction RA %	Resilienza Kerbschlagarbeit Impact Value Resilience	Durezza Härte Hardness Dureté HB		
Valori richiesti		min		30	-	75	-	40	-	50	-	140
Anforderungen/Required values		max				115						223
A	12,5	68	L	39		84		64		75		165

TEST ALLO STATO DI FORNITURA			
Test on delivery condition / Prüfung auf lieferbarem produkt / Test a l'etat de fourniture / Prueba sobre el material así como entregado			
TEST	min	max	
A	Grain size for ASTM E112		4

Mechanical properties according to ASTM A370.

Analisi chimica												
Chemische Zusammensetzung/Chemical Analysis/Analyse chimique												
Colata /Heat	min	-	1,25	16,50	2,00	10,00	-	-	0,020	-	-	-
Schmelze/Couée	max	0,030	1,00	2,00	18,00	3,00	1,00	14,00	-	0,040	0,030	0,100
	C %	Si %	Mn %	Cr %	Mo %	Cu %	Ni %	Co %	P %	S %	N %	
273944	0,015	0,41	1,69	16,78	2,03	0,52	10,00	0,107	0,029	0,023	0,085	

Corrosion test in 16% sulfuric acid and copper sulfate solutions							
Test standard: ASTM A262-Practice E							
Test	Heat treatment before test	Length of Period (h)	Test temp (°C)	Bend Angle (°)	Ø spindle (mm)	Result of visual inspection at 20 x magnification after bend test	Result
Intergranular corrosion	Sensitization	15	boil	180	5	Absence of cracks	SATISFACTORY

Corrosion test in 16% sulfuric acid and copper sulfate solutions							
Test standard: ASTM A262-Practice E							
Test	Heat treatment before test	Length of Period (h)	Test temp (°C)	Bend Angle (°)	Ø spindle (mm)	Result of visual inspection at 20 x magnification after bend test	Result
Intergranular corrosion	Sensitization	15	boil	180	5	Absence of cracks	SATISFACTORY

C193764



Acciaierie Valbruna S.p.A.

36100 VICENZA (Italia) - Viale della scienza, 25 z.i.
 Telefono 0444.968211 - Fax 0444.963836
 Stab.: 39100 BOLZANO (Italia) - Via A. Volta, 4/37
 Telefono 0471.924111 - Fax 0471.924497

CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a: EN 10204 (2004), 3.1 / ISO 10474 (2013), 3.1

Certificato nr. MEST115628 / 2017 /

Nach/According to/Selon

Prüfung/Test/Essai

Cliente / Bestaller/Purchaser/Cliënt
 VALBRUNA CANADA LTD
 8724 HOLGATE CRESCENT
 L5T 5Z1 - MILTON, ONT L5T 5Z1 - CA

Stato di fornitura: Forged - Annealed FORGED
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore:
 Hersteller/Item/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: 705006370 Stock - Canada

Bestell
 Your order
 Commande

Tipo di Elaborazione: E+AOD
 Erschmelzungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de fusine productrice



Conferma ordine nr: EI17005543

Werkz/Our Order/Ref. nr.

Qualità: 316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'assesseur

MR

Avviso di Spedizione: D-V117023377
 Lieferanzeige/Packing list/B.L.

Marca: APML
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 316/316L
 Kennzeichnung
 Marking
 Marquage

Produced without class I-II Ozone depleting substances.
 Solution heat treated free from continuous carbide network.
 Annealing temperature : 1940° F for 4 h/water.
 Micro and macro etch test : OK
 Reduction ratio = 7,6 : 1
 Material is DFARS Compliant

Sono state soddisfatte tutte le condizioni richieste
 Die gestellten Anforderungen sind erfüllt, Anlage erfüllt
 The material has been furnished in accordance with the requirements
 Le matériel a été trouvé conforme aux exigences

Controllo antimiscelazione: OK
 Verwechslungsprüfung: spektroskopisch durchgeführt
 Antimixing testing performed: OK
 Contrôle antimélange fait: r.s.s.

Controllo visivo e dimensionale: soddisfa le esigenze
 Besichtigung und Ausmessung: ohne Beanstandung
 Visual inspection and dimensional checks: satisfactory
 Contrôle visuel et dimensions: satisfaisant

Melted and manufactured in Italy No welding or weld repair Material free from Mercury contamination

We declare that the finished product is checked for radioactive contamination through Portal System when it leaves the production plant.

QUALITY MANAGEMENT SYSTEM CERTIFIED BY LLOYD'S REGISTER ACCORDING TO ISO 9001 : 2008, ISO/TS16949 : 2009, AS 9100C

The Quality Management System is Certified acc. Pressure Equipment Directive [97/23/EC] Annex 1, s., 4.3 and 2014/68/EU by TUEV and LLOYD'S
 Any act of tampering, modification, alteration, counterfeiting and/or falsification and/or any other action which modifies the contents of this test certificate shall constitute a violation of applicable civil and criminal laws. Acciaierie Valbruna shall protect its rights and interests before any competent court, authority and jurisdiction.
 Maximal and/or Valplus grades/products are manufactured with ladle techniques to control composition, distribution, size and shape of non-metallic inclusions for improved machinability.
 The supplied product conforms to requirements expressly requested by the purchaser and conforms to requirements specified by certified norms and standards. Should the product be used for more severe, critical and/ or in any case different applications than those the material is generally intended for, any different and/or supplementary requirements shall be specifically demanded, at least, upon order of the Product by the Purchaser. Acciaierie Valbruna SpA shall not be responsible for any improper use of the Products.