


82 pcs I283777
C302652

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№ 3055/PO51518 DIN EN 10088-3-05, DIN EN 10272-08, AD2000-Merkblatt W2; AD 2000-Merkblatt W10; ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10GR B8M, CL1; ASME SA-193/SA-193M-10 GR B8, CL 1; ASTM A320/A320M-08 GR B8M, CL 1; ASME SA-320/SA-320M-10 GR B8M, CL 1; NACE MR 0175-03; NACE MR 0103-10	Sheets: 3 Sheet: 1 INSPECTION CERTIFICATE EN10204/3.1 Nr. 371973 PLANT ORDER № 8014903055
---	--	---

	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line. Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, обточенные на линии Ландграф. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 5.000in/127.00 mm L=5.300/17.000ft L=5.080m/17.000ft Grade: 316/316L/1.4401/1.4404	QUANTITY: (number of pcs)	1bund Q-5957lb/2702 kg 1bund Q-1160lb/526 kg
			Delivery condition solution annealed :1900° F(1040°C)water 30minutes термообработка:закалка в воду	

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<10	<.40	<.10	<20	<15	<.40	<.20	<.10		
CAST № A10115	.020	.43	1.33	.040	.022	16.78	10.19	2.06	.073	.28	.05	.06	.005	.10	.01	.034	.009	.0023

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS:																				
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z% L	Brinell Hardness HB	Impact strength, KV, J		Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 3.0 2.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order Ratio of reduction-22.3:1																				
	L	Q		In 2 inches (50mm) or 4D,min,% L	L			L	L											Q										
REQUIRED	205	240	515-700	40	-	40	50	140-217	100											-										
EFFECTIVE	286 291	315 323	580 580	61	-	58 59	75 77	170 170	220 224											220 224	220 224									

US - testing	yes	Results: ASTM A388/A388M-FBH1/8"; EN 10308 type 1a; class 3:OK	Date: 20.07.2021 Manager of quality assurance department - V. Kapaieva Signed: Zaporozhye Melted and Produced in Ukraine. MELTED and MANUFACTURED PrJSC " Dnipropetsstal" Phone number +380612834255 e-mail: info@dss.com.ua http://www.dss-ua.com
Radiation free; mercury free. No Weld or Weld repair.			



ANS