



C303497

PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№ 3055/PO51518 DIN EN 10088-3-05, DIN EN 10272 08, AD2000-Merkblatt W2; AD 2000-Merkblatt W10, ASTM A182/A182M-10; ASME SA-182/SA-182M-10; ASTM A276-10; ASTM A314-08, ASTM A479/A479M-10; ASME SA-479/SA-479M-10; ASTM A484/A484M-10; AMS-QQ-S-763B-06 Cond.A; AMS 5648K-07; AMS 5653F-07; ASTM A193/A193M-10 GR B8M, CL1 (EXC PAR 7.2); ASME SA-193/SA-193M-10 GR B8, CL 1 (EXC PAR 7.3); NACE MR 0175-03; NACE MR 0103-10	Sheets: 2 Sheet: 1 INSPECTION CERTIFICATE EN10204/3.1 Nr. 372531 PLANT ORDER № 8014903055
---	---	---

	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line. Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, обточенные на линии Ландграф. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ: Электродуговая печь+АКР Round 3.750m/95.25 mm L=4.720/15.000ft Grade: 316/316L/1.4401/1.4404	QUANTITY: (number of pcs) 1bund Q-5935lb/2692kg Delivery condition solution annealed : 1900°F (1040°C) water 30minutes термообработка: закалка в воду
---	--	---	--

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1.00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A10116	.023	.41	1.34	.040	.024	16.90	10.28	2.05	.064	.33	.06	.05	.005	.14	.01	.030	.0104	.0024

DIN EN 10002-1, ASTM A370-09										TECHNICAL REQUIREMENTS: Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) <table style="width:100%; text-align: center;"> <tr> <td>A</td><td>B</td><td>C</td><td>D</td><td></td><td></td><td></td><td></td> </tr> <tr> <td>thin</td><td>thick</td><td>thin</td><td>thick</td><td>thin</td><td>thick</td><td>thin</td><td>thick</td> </tr> <tr> <td>3.0</td><td>2.0</td><td>2.0</td><td>2.0</td><td>0.0</td><td>0.0</td><td>1.0</td><td>1.0</td> </tr> </table> ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order Ratio of reduction-35.1:1										A	B	C	D					thin	thick	thin	thick	thin	thick	thin	thick	3.0	2.0	2.0	2.0	0.0	0.0	1.0	1.0
A	B	C	D																																								
thin	thick	thin	thick	thin	thick	thin	thick																																				
3.0	2.0	2.0	2.0	0.0	0.0	1.0	1.0																																				
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J																																			
	L	Q		Δ, % L	In 2 inches (50mm) or 4D, min, % L			L	Q																																		
REQUIRED	205	240	515-700	40	-	40	50	140-217	100	-																																	
EFFECTIVE	296 300	337 331	564 568	60	-	58 58	78 78	163 163	203 203 203 201 201 201	-																																	

US - testing	yes	Results: ASTM A388/A388M-FBII1/8"; EN 10308 type 1a; class 3:OK	Date: 04.08.2021 Manager of quality assurance department - V. Kapaieva Signed: Zaporozhye Melted and Produced in Ukraine. MELTED and MANUFACTURED PrJSC " Dniprospetsstal" Phone number +380612834255 e-mail: info@dss.com.ua http://www.dss-ua.com
--------------	-----	---	---

Radiation free; mercury free. No Weld or Weld repair.

