



PrJSC DNIPROSPETSSTAL, YUZHNOYE SHOSSE 81, 69008 ZAPOROZHYE, UKRAINE

	Contract No.: 20002 TECHN.PROTOCOL № 390-11 SPEC.№ 3880/PO52069 DIN EN 10088-3-05,DIN EN 10272-08,AD2000-Merkblatt W2;AD 2000-Merkblatt W10;ASTM A182/A182M-10;ASME SA-182/SA-182M-10;ASTM A276-10;ASTM A314-08,ASTM A479/A479M-10;ASME SA-479/SA-479M-10;ASTM A484/A484M-10;AMS-QQ-S-763B-06 Cond.A;AMS 5648K-07;AMS 5653F-07;ASTM A193/A193M-10GR B8M,CL1(EXC PAR 7.2); ASME SA-193/SA-193M-10 GR B8,CL 1(EXC PAR 7.3);NACE MR 0175-03;NACE MR 0103-10	INSPECTION CERTIFICATE EN10204/3.1 Nr. 375870 PLANT ORDER № 8014903880	
	CUSTOMER DSS INTERNATIONAL SA Switzerland	PRODUCT DESCRIPTION Bars and rods of corrosion-resistant (stainless) steel hot rolled, peeled on Landgraf line.Прутки из коррозионностойких (нержавеющих) сталей горячекатаные, обточенные на линии Ландграф. STEEL MAKING PROCESS: EAF+AOD СПОСОБ ВЫПЛАВКИ:Электродуговая печь+АКР Round 3.750in/95.25 mm L=3.740/12.262ft L=5.650m/18.525ft L=5.640/18.492ft Grade: 316/316L/1.4401/1.4404	QUANTITY: (number of pcs) 1bund Q-961 lb/4362kg 1bund Q-2892 lb/1312kg 1bund Q-2892 lb/1312kg Delivery condition solution annealed :1900° F(1040°C)water 30minutes термообработка:закалка в воду

ANALYSIS, %	C	Si	Mn	P	S	Cr	Ni	Mo	Al	Cu	V	W	Ti	Co	Nb	N	Sn	B
REQUIRED	<.030	<1,00	1.20-2.00	<.040	.015-.030	16.50-18.00	10.00-13.00	2.00-2.50	<.10	<.40	<.10	<.20	<.15	<.40	<.20	<.10		
CAST № A10595	.025	.49	1.31	.038	.027	16.67	10.22	2.05	.075	.29	.05	.10	.006	.14	.01	.028	.009	.0024

DIN EN 10002-1,ASTM A370-09										TECHNICAL REQUIREMENTS: Macrostructure – GOOD GRAIN SIZE : 5 to ASTM E 112-96(2004) Nonmetallic inclusions ASTM E 45-05 (Method A) A B C D thin thick thin thick thin thick thin thick 3.0 2.0 2.0 1.0 0.0 0.0 1.0 1.0 ICC-ASTM A262-08 (practice E)-test: O.K. Dimension/surface defects test, anti-mixing test – OK We acknowledge that the delivered products conform to the requirements of the order Ratio of reduction-35.1:1									
MECHANICAL PROPERTIES	Yield Strength, (N/mm ²) R0.2% R 1.0%		Tensile Strength, Rm, (N/mm ²)	Elongation		Reduction of area, Z % L	Brinell Hardness HB	Impact strength, KV, J											
	L	Q		A ₅ % L	In 2 inches (50mm) or 4D,min,% L			L	Q										
REQUIRED	205	240	515-690	40	-	40	50	140-217	100										
EFFECTIVE	275	316	540	58	-	57	75	163	201 201 201	-									
Mechanical properties tested in state of delivery																			

US - testing	yes	Results: ASTM A388/A388M-FBH1/8";EN 10308 type 1a;class 3:OK	Date: 30.11.2021 Manager of quality assurance department - V. Kapaieva Signed: Zaporozhye Melted and Produced in Ukraine. MELTED and MANUFACTURED PrJSC " Dnipropetsstal" Phone number +380612834255 e-mail: info@dss.com.ua http://www.dss-ua.com
Radiation free; mercury free. No Weld or Weld repair.			